




PRODUKTBESCHREIBUNG

- » Freigestellt nach der Schneide
- » Hochleistungs-Fräser mit Zentrumsschnitt für 3D-Bearbeitung

MATERIAL


» VHM, TiAlSiN-beschichtet



Z	d2	d3	l	l1	l2	l3	w	d	R	Nr.	EUR
2	0,48	4	50	1	20	3	4,6	0,5	0,1	WZF 17416/ 0,5/0,1	< >
2	0,95	4	50	2	20	6	4	1	0,2	WZF 17416/ 1 /0,2	< >
2	1,9	6	57	3	21	8	5,6	2	0,2	WZF 17416/ 2 /0,2	< >
2	1,9	6	57	3	21	8	5,6	2	0,5	WZF 17416/ 2 /0,5	< >
2	2,8	6	57	3,5	21	14	4,2	3	0,3	WZF 17416/ 3 /0,3	< >
2	2,8	6	57	3,5	21	14	4,2	3	0,5	WZF 17416/ 3 /0,5	< >
2	3,8	6	57	4	21	16	2,9	4	0,3	WZF 17416/ 4 /0,3	< >
2	3,8	6	57	4	21	16	2,9	4	0,5	WZF 17416/ 4 /0,5	< >
2	3,8	6	57	4	21	16	2,9	4	1	WZF 17416/ 4 /1	< >
2	4,8	6	57	5	21	18	1,4	5	0,5	WZF 17416/ 5 /0,5	< >
2	4,8	6	57	5	21	18	1,4	5	1	WZF 17416/ 5 /1	< >
2	5,7	6	57	6	21	-	-	6	0,5	WZF 17416/ 6 /0,5	< >
2	5,7	6	57	6	21	-	-	6	1	WZF 17416/ 6 /1	< >
2	5,7	6	57	6	21	-	-	6	2	WZF 17416/ 6 /2	< >
2	7,7	8	63	8	27	-	-	8	0,5	WZF 17416/ 8 /0,5	< >
2	7,7	8	63	8	27	-	-	8	1	WZF 17416/ 8 /1	< >
2	9,5	10	72	10	32	-	-	10	0,5	WZF 17416/10 /0,5	< >
2	9,5	10	72	10	32	-	-	10	1	WZF 17416/10 /1	< >
2	9,5	10	72	10	32	-	-	10	2	WZF 17416/10 /2	< >
2	9,5	10	72	10	32	-	-	10	3	WZF 17416/10 /3	< >
2	11,5	12	83	12	38	-	-	12	2	WZF 17416/12 /2	< >


RICHTWERTE SCHRUPPEN

WZF 17416	Werkstoff	Festigkeit	Vc ¹ m/min.	d							
				≤ 1	2	3	4	6	8	10	12
				fz ² (mm/z)							
1.1730	640 N/mm ²	200	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2083	780 N/mm ²	130	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2083	52 HRC	90	0.005	0.020	0.030	0.035	0.040	0.050	0.070	0.080	
1.2085	1080 N/mm ²	130	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2162	660 N/mm ²	200	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2162	52 HRC	110	0.005	0.020	0.030	0.035	0.040	0.050	0.070	0.080	
1.2311	1080 N/mm ²	145	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2312	1080 N/mm ²	150	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2316	1010 N/mm ²	130	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2343	780 N/mm ²	160	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2343	52 HRC	110	0.005	0.020	0.030	0.035	0.040	0.050	0.070	0.080	
1.2379	780 N/mm ²	130	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2714HH	1350 N/mm ²	130	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2767	830 N/mm ²	150	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2767	52 HRC	110	0.005	0.020	0.030	0.035	0.040	0.050	0.070	0.080	
1.2842	775 N/mm ²	150	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
Stahl	1400 N/mm ²	130	0.005	0.020	0.030	0.035	0.040	0.050	0.070	0.080	
ap (mm)			0.07	0.15	0.20	0.30	0.40	0.60	0.75	1.00	
ae (mm)			0.30	1.00	1.50	2.00	3.00	4.00	5.00	6.00	



RICHTWERTE SCHLICHTEN

WZF 17416	Werkstoff	Festigkeit	Vc ¹ m/min.	d							
				≤ 1	2	3	4	6	8	10	12
				fz ² (mm/z)							
1.1730	640 N/mm ²	300	0.005	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2083	780 N/mm ²	195	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2083	52 HRC	140	0.005	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2085	1080 N/mm ²	195	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2162	660 N/mm ²	300	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2162	52 HRC	200	0.005	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2311	1080 N/mm ²	220	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2312	1080 N/mm ²	225	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2316	1010 N/mm ²	180	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2343	780 N/mm ²	240	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2343	52 HRC	200	0.005	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2379	780 N/mm ²	195	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2714HH	1350 N/mm ²	180	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2767	830 N/mm ²	225	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2767	52 HRC	200	0.005	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
1.2842	775 N/mm ²	225	0.008	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
Stahl	1400 N/mm ²	180	0.005	0.030	0.040	0.045	0.050	0.070	0.100	0.120	
ap (mm)			0.03	0.08	0.11	0.13	0.15	0.20	0.30	0.40	
ae (mm)			0.10	0.20	0.30	0.40	0.70	1.00	1.50	2.00	



1) Vc: Schnittgeschwindigkeit (m/min.)

2) fz: Vorschub pro Schneide (mm/z)

i Weitere Materialien und Schnittwerte finden Sie im Schnittdaten-Kalkulator